











## 109 年市售咖啡外帶紙杯測試彙整表

項次	樣品編號	樣品名稱	檢驗報告編號	樣品照片	特定元素遷移測試	顏色遷移性測試
1	1090926AR7843-001	外帶咖啡杯	HTT20A00058	<p style="text-align: center;"><b>HTT20A00058</b></p> 	溶出鋁：588 ppm 其餘元素：均為 n.d.	無顏色遷移現象
2	1090926AR7843-002	12OZ 墨內杯	HTT20A00059	<p style="text-align: center;"><b>HTT20A00059</b></p> 	溶出鋁：508 ppm 其餘元素：均為 n.d.	無顏色遷移現象
3	1090926AR7843-003	現萃茶紙杯(大)-綠	HTT20A00060	<p style="text-align: center;"><b>HTT20A00060</b></p> 	溶出鋁：467 ppm 其餘元素：均為 n.d.	無顏色遷移現象
4	1090926AR7843-004	外帶咖啡杯	HTT20A00061	<p style="text-align: center;"><b>HTT20A00061</b></p> 	溶出鋁：349 ppm 其餘元素：均為 n.d.	無顏色遷移現象
5	1090926AR7843-005	冷熱共用杯	HTT20A00062	<p style="text-align: center;"><b>HTT20A00062</b></p> 	溶出鋁：425 ppm 其餘元素：均為 n.d.	無顏色遷移現象

項次	樣品編號	樣品名稱	檢驗報告編號	樣品照片	特定元素遷移測試	顏色遷移性測試
6	1090926AR7843-006	咖啡杯	HTT20A00063	<p>HTT20A00063</p> 	溶出鋁：392 ppm 其餘元素：均為 n.d.	無顏色遷移現象
7	1090926AR7843-007	咖啡杯	HTT20A00064	<p>HTT20A00064</p> 	溶出鋁：489 ppm 其餘元素：均為 n.d.	無顏色遷移現象
8	1090926AR7843-008	外帶咖啡杯	HTT20A00065	<p>HTT20A00065</p> 	溶出鋁：556 ppm 其餘元素：均為 n.d.	無顏色遷移現象
9	1090930AO0481-001	外帶咖啡杯	HTT20A00066	<p>HTT20A00066</p> 	溶出鋁：470 ppm 其餘元素：均為 n.d.	無顏色遷移現象
10	1090930AO0481-001	外帶咖啡杯	HTT20A00067	<p>HTT20A00067</p> 	溶出鋁：416 ppm 其餘元素：均為 n.d.	無顏色遷移現象

n.d.=Not Detected(未檢出)